

UL INTERNATIONAL (UK) LTD Wonersh House, Building C, The Guildway, Old Portsmouth Road, Guildford. GU3 1LR. United Kingdom.





designated according to Article 29 of the Regulation (EU) No 305/2011 and member of EOTA (European Organisation for Technical Assessment, www.eota.eu)

European Technical Assessment

ETA 14/0318 of 22/08/2014

Technical Assessment Body issuing the ETA and designated according to Article 29 of the Regulation (EU) No 305/2011: UL International (UK) Ltd

Product family to which the construction product belongs

Fire Stopping and Sealing Product:

Penetration Seals

Manufacturer Joints L.R. Oy.

Teollisuustie 6 51200 Kangasniemi

Finland

Manufacturing plant(s) A/007

This European Technical Assessment 13 pages including 1 Annex which forms an

contains integral part of this assessment.

This European Technical Assessment is issued in accordance with regulation (EU) No 305/2011, on the basis of

Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and should be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full. However, partial reproduction may be made, with the written consent of the issuing Technical Assessment Body. Any partial reproduction has to be identified as such.

Table of Contents

I.	SPI	ECIFIC PAR	RTS OF THE EUROPEAN TECHNICAL ASSESSMENT	3
1			l description of the product	
2	2	Specifica	tion of the intended uses of the product in accordance with the applicable European Assessment Document (Hereinafte AG 026-2	r
3	3	Performa	ance of the product and references to the methods used for its assessment	5
4	1		IENT AND VERIFICATION OF CONSTANCY OF PERFORMANCE (HEREINAFTER AVCP) SYSTEM APPLIED, WITH REFERENCE TO L BASE	
5	5	Technica	l details necessary for the implementation of the AVCP system, as provided for in the applicable EAD	6
6	5	Issued or	1:	7
ANI	NEX A	– Resista	nce to Fire Classification – Joints Fire Collar Pro+	8
ļ	٨.1	Flexible o	or rigid wall constructions with wall thickness of minimum 100 mm	8
	A.1	l.1	Penetration seals, in drywalls and concrete/masonry walls	8
A	٨.2	Rigid wal	ls constructions with wall thickness of minimum 150 mm	10
	A.2	2.1	Penetration seals, in concrete/masonry walls	10
A	٨.3	Rigid floo	or constructions with floor thickness of minimum 150 mm	11
	A.3	3.1	Penetration seals, surface mounted in concrete floors	11
	A.3	3.2	Penetration seals, cast into concrete floors	12
A	٨.4	Rigid floo	or constructions with floor thickness of minimum 250 mm	13
	A.4	1.1	Penetration seals, surface mounted in concrete floors	13

I. SPECIFIC PARTS OF THE EUROPEAN TECHNICAL ASSESSMENT

1 Technical description of the product

- 1) Joints Fire Collar Pro+ is a pipe closure device used to form penetration seals where combustible pipes, cables and metal pipes with insulation penetrate walls and floors.
- 2) The Joints Fire Collar Pro+ is supplied with intumescent liner complete within metal steel shell, to be clamped around the service and screw fixed back to the supporting element. The Joints Fire Collar Pro+ may be supplied with powder coated steel or stainless steel shells.
- 3) The applicant has submitted a written declaration that the product and/or constituents of the product contains no substances which have been classified as dangerous according to Directive 67/548/EEC and Regulation (EC) No. 1272/2008 and listed in the 'indicative list on dangerous substances' of the EGDS taking into account the installation conditions of the construction product and the release scenarios resulting from there.

In addition to the specific clauses relating to dangerous substances contained in this European Technical Assessment, there may be other requirements applicable to the products falling within its scope (e.g. transposed European legislation and national laws, regulations and administrative provisions). In order to meet the provisions of the Construction Products Regulation, these requirements need also to be complied with, when and where they apply.

4) The use catagory of Joints Fire Collar Pro+ in relation to BWR 3 (Hygiene, health and environment) is IA1, S/W3

2 Specification of the intended uses of the product in accordance with the applicable European Assessment Document (Hereinafter EAD): ETAG 026-2

Detailed information and data is given in Annex A.

The intended use of system Joints Fire Collar Pro+ is to reinstate the fire resistance performance of flexible wall and rigid wall and floor constructions, where they are penetrated by services.

1) The specific elements of construction that the system Joints Fire Collar Pro+ may be used to provide a penetration seal in, are as follows:

Flexible walls: The wall must have a minimum thickness of 100 mm and comprise steel studs

lined on both faces with minimum 2 layers of 12.5 mm thick boards.

Rigid walls: The wall must have a minimum thickness of 100 mm and comprise concrete,

aerated concrete or masonry, with a minimum density of 650 kg/m3.

Rigid floors: The floor must have a minimum thickness of 150 mm and comprise aerated

concrete or concrete with a minimum density of 650 kg/m3.

The supporting construction must be classified in accordance with EN 13501-2 for the required fire resistance period.

2) The system Joints Fire Collar Pro+ may be used to provide a penetration seal with specific supporting constructions and substrates (for details see Annex A).

- The provisions made in this European Technical Assessment are based on an assumed working life of the Joints Fire Collar Pro+ of 10 years, provided that the conditions laid down in the manufacturers datasheet and instructions for the packaging/transport/storage/installation/use/repair are met. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.
- Type Z_2 : intended for use at internal conditions with humidity classes other than Z1, excluding temperatures below 0°C.

3 Performance of the product and references to the methods used for its assessment

Product-type: Pipe Collar		Intended use: Penetration Seal	
Basic requirement for construction work	Basic Requ	uirement	Performance
	BWR 1 Mechanical re	sistance and stabilit	у
-	Nor	Not relevant	
	BWR 2 Safety	in case of fire	
EN 13501-1	Reaction	n to fire	Class F
EN 13501-2	Resistanc	ce to fire	Annex A
	BWR 3 Hygiene, hea	Ith and environment	
EN 1026:2000	Air permeability (r	material property)	No performance determined
ETAG 026-2, Annex C	Water permeability	(material property)	No performance determined
Declaration of manufacturer	Release of dangerous substances		Use categories: IA1, S/W3 Declaration of manufacturer
	BWR 4 Sat	fety in use	1
EOTA TR 001:2003	Mechanical resistance and stability		No performance determined
EOTA TR 001:2003	Resistance to impact/movement		No performance determined
EOTA TR 001:2003	Adhesion		No performance determined
	BWR 5 Protection	on against noise	
EN 10140-2/ EN ISO 717-1	Airborne sou	nd insulation	No performance determined
	BWR 6 Energy econor	ny and heat retention	on
EN 12664, EN 12667 or EN 12939	Thermal p	properties	No performance determined
EN ISO 12572 EN 12086	Water vapour	permeability	No performance determined
General aspects relating to fitness for use			
EOTA TR 024:2009, clause 3.1.11 & 3.1.12 Durability and		serviceability	Z ₂
BWR 7 Sustainable use of natural resources			
-	-		No performance determined

4 ASSESSMENT AND VERIFICATION OF CONSTANCY OF PERFORMANCE (HEREINAFTER AVCP) SYSTEM APPLIED, WITH REFERENCE TO ITS LEGAL BASE

According to the decision 1999/454/EC – Commission Decision of date 22nd June 1999 on on the procedure for attesting the conformity of construction products pursuant to Article 20(2) of Council Directive 89/106/EEC as regards fire stopping, fire sealing and fire protective products, published in the Official Journal of the European Union (OJEU) L178/52 of 14/07/1999, see http://eur-lex.europa.eu/JOIndex.do) of the European Commission¹, as amended, the system(s) of assessment and verification of constancy of performance (see Annex V to Regulation (EU) No 305/2011) given in the following table(s) applies (apply).

Product(s)	Intended use(s)	Level(s) or class(es)	System(s)
Fire stopping and Fire Sealing Products	For fire compartmentation and/or fire protection or fire performance	Any	1

5 <u>Technical details necessary for the implementation of the AVCP system, as provided for in the applicable EAD</u>

Tasks of the manufacturer:

Factory production control

The manufacturer shall exercise permanent internal control of production. All the elements, requirements and provisions adopted by the manufacturer shall be documented in a systematic manner in the form of written policies and procedures, including records of results performed. This production control system shall ensure that the product is in conformity with this European Technical Assessment.

The manufacturer may only use initial / raw / constituent materials stated in the technical documentation of this European Technical Assessment.

The factory production control shall be in accordance with the Control Plan of 6th May 2014 relating to the European Technical Assessment ETA 14/0318 issued on 22/08/14 which is part of the technical documentation of this European Technical Assessment. The "Control Plan" is laid down in the context of the factory production control system operated by the manufacturer and deposited at UL International (UK) Ltd.

The results of factory production control shall be recorded and evaluated in accordance with the provisions of the Control Plan.

¹ Official Journal of the European Communities L178/52 of 14/7/1999

Other tasks of the manufacturer

Additional information

The manufacturer shall provide a technical data sheet and an installation instruction with the following minimum information:

- (a) Technical data sheet:
 - Field of application:
 - Building elements for which the penetration seal is suitable, type and properties of the building elements like minimum thickness, density, and - in case of lightweight constructions – the construction requirements.
 - Limits in size, minimum thickness etc. of the penetration seal
 - Construction of the penetration seal including the necessary components and additional products (e.g. backfilling material) with clear indication whether they are generic or specific.
- (b) Installation instruction:
 - Steps to be followed
 - Procedure in case of retrofitting
 - Stipulations on maintenance, repair and replacement

6 <u>Issued on:</u>

22nd August 2014

Report by:

Reviewed by:

C. Johnson Staff Engineer

Building and Life Safety Technologies


C. W. Miles

Business Manager – Europe & Latin America Building and Life Safety Technologies

For and on behalf of UL International (UK) Ltd.

ANNEX A - Resistance to Fire Classification - Joints Fire Collar Pro+

- A.1 Flexible or rigid wall constructions with wall thickness of minimum 100 mm
- A.1.1 Penetration seals, in drywalls and concrete/masonry walls



A.1.1.1

Services	Collar Inlay	Classification	
PVC-U pipe according to EN 1329-1, EN			
1452-2 and EN 1453-1^			
Diameter 110 mm, wall thickness 3.0 mm	50 x 8.0 mm	E 90 U/C, E 90 C/C	
		EI 60 U/C, EI 60 C/C	
Diameter 125 mm, wall thickness 3.5 mm	60 x 12 mm	EI 90 U/C, EI 90 C/C	
Diameter 160 mm, wall thickness 3.2 mm	60 x 12 mm	E 120 U/C, E 120 C/C	
Diameter 100 mm, wan thickness 3.2 mm	00 X 12 IIIIII	EI 90 U/C, EI 90 C/C	
Diameter 160 mm, wall thickness 4.5 mm	60 x 16 mm	E 90 U/C, E 90 C/C	
	00 X 10 IIIIII	EI 60 U/C, EI 60 C/C	
Diameter 315 mm, wall thickness 9.2 mm	75 x 18 mm	EI 60 C/C	
PE pipe according to EN 1519-1, EN 12201-2 and EN 12666-1 ^{\$}			
Diameter 200 mm, wall thickness 18.2	75 x 10.8 mm		
mm		EL CO C/C	
Diameter 250 mm, wall thickness 22.7	75 42.6	EI 60 C/C	
mm	75 x 12.6 mm		
PP pipe according to EN 1451-1			
Diameter 50 mm, wall thickness 2.5 mm	50 x 4.0 mm	EI 90 U/C, EI 90 C/C	
Diameter 75 mm, wall thickness 3.5 mm	50 x 6.0 mm*	EI 60 U/C, EI 60 C/C	


^{* 82} mm diameter collar

^{\$} In Germany the pipes have additionally to comply with DIN 19535-10

[^] In Germany the pipes have additionally to comply with DIN 19531-10

A.2 Rigid walls constructions with wall thickness of minimum 150 mm

A.2.1 Penetration seals, in concrete/masonry walls



A.2.1.1


Services	Collar Inlay	Classification	
PVC-U pipe according to EN 1329-1, EN			
1452-2 and EN 1453-1*			
Diameter 315 mm, wall thickness 9.2 mm	75 x 18 mm	EI 120 C/C	
PE pipe according to EN 1519-1, EN 12201-2 and EN 12666-1 [^]			
Diameter 200 mm, wall thickness 18.2 mm	75 x 10.8 mm	EI 60 C/C	
Diameter 250 mm, wall thickness 22.7 mm	75 x 12.6 mm	E 120 C/C	
Diameter 250 mm, wan thickness 22.7 mm	75 X 12.0 IIIIII	EI 90 C/C	

^{*} In Germany the pipes have additionally to comply with DIN 19531-10

[^]In Germany the pipes have additionally to comply with DIN 19535-10

A.3 Rigid floor constructions with floor thickness of minimum 150 mm

A.3.1 Penetration seals, surface mounted in concrete floors



A.3.1.1

Services	Collar Inlay	Classification	
PVC-U pipe according to EN 1329-1, EN			
1452-2 and EN 1453-1 [^]			
Diameter 110 mm, wall thickness 3.0 mm	50 x 8.0 mm	EI 90 U/C, EI 90 C/C	
Diameter 140 mm, wall thickness 6.0 mm	60 x 16 mm*	EI 120 U/C, EI 120 C/C	
Diameter 160 mm, wall thickness 4.0 mm	60 x 16 mm	El 120 0/C, El 120 C/C	
PP pipe according to EN 1451-1			
Diameter 110 mm, wall thickness 3.8 mm	50 x 8.0 mm	EI 240 U/C, EI 240 C/C	
PE pipe according to EN 1519-1, EN 12201-2 and EN 12666-1 ^{\$}			
Diameter 125 mm, wall thickness 9.0 mm	60 x 12 mm	E 120 U/C, E 120 C/C	
Diameter 125 mm, wall thickness 8.0 mm		EI 90 U/C, EI 90 C/C	
Diameter 160 mm, wall thickness 10 mm	60 x 16 mm	EI 60 U/C, EI 60 C/C	

^{* 160} mm diameter collar

 $^{{}^{\$}\}mbox{In Germany}$ the pipes have additionally to comply with DIN 19535-10

[^] In Germany the pipes have additionally to comply with DIN 19531-10

A.3.2 Penetration seals, cast into concrete floors

Penetration Seal: Combustible pipes fitted with Joints Fire Collar Pro+, cast into the soffit of the floor (fire side only).


Construction details:

A.3.2.1

Services	Collar Inlay	Classification
ABS pipe according to EN 1455-1		
Diameter 110 mm, wall thickness 5.3 mm	50 x 8.0 mm	EI 180 U/C, EI 180 C/C

A.4 Rigid floor constructions with floor thickness of minimum 250 mm

A.4.1 Penetration seals, surface mounted in concrete floors



A.4.1.1

Services	Collar Inlay	Classification	
PVC-U pipe according to EN 1329-1, EN			
1452-2 and EN 1453-1*			
Diameter 110 mm, wall thickness 3.0 mm	50 x 8.0 mm	EI 240 U/C, EI 240 C/C	
Diameter 125 mm, wall thickness 3.5 mm	60 x 12 mm	EI 120 U/C, EI 120 C/C	
Diameter 160 mm, wall thickness 4.5 mm	60 x 16 mm	EI 90 U/C, EI 90 C/C	
PP pipe according to EN 1451-1			
Diameter 50 mm, wall thickness 2.5 mm	50 x 4.0 mm	EI 240 U/C, EI 240 C/C	
Diameter 75 mm, wall thickness 3.5 mm	50 x 6.0 mm ^{\$}	EI 240 0/C, EI 240 C/C	

^{\$ 82} mm diameter collar

^{*} In Germany the pipes have additionally to comply with DIN 19531-10